


Technylstar™ S 218 V30



PA6-GF30

Solvay Engineering Plastics


Product Texts

Technylstar Polyamide, reinforced with 30% of glass fibre Characterized by high fluidity of the melt.

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	9600 / 6200	MPa	ISO 527-1/-2
Stress at break	180 / -	MPa	ISO 527-1/-2
Strain at break	3.2 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	81 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / -	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205 / *	°C	ISO 75-1/-2
Other properties			
ISO Data			
Water absorption	0.95 / *	%	Sim. to ISO 62
Density	1340 / -	kg/m ³	ISO 1183

Diagrams
Viscosity-shear rate

Shearstress-shear rate


Stress-strain



Characteristics

Processing

Injection Molding

Other text information

Injection Molding

PROCESSING

Melt temperature: 220°C

Mold temperature: 80°C

Chemical Media Resistance

Acids

- ☺ Acetic Acid (5% by mass) (23°C)
- ☺ Citric Acid solution (10% by mass) (23°C)
- ☺ Lactic Acid (10% by mass) (23°C)
- ☹ Hydrochloric Acid (36% by mass) (23°C)
- ☹ Nitric Acid (40% by mass) (23°C)
- ☹ Sulfuric Acid (38% by mass) (23°C)
- ☹ Sulfuric Acid (5% by mass) (23°C)
- ☹ Chromic Acid solution (40% by mass) (23°C)

Bases

- ☹ Sodium Hydroxide solution (35% by mass) (23°C)
- ☺ Sodium Hydroxide solution (1% by mass) (23°C)
- ☺ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ☹ Isopropyl alcohol (23°C)
- ☹ Methanol (23°C)
- ☹ Ethanol (23°C)

Hydrocarbons

- ☺ n-Hexane (23°C)
- ☺ Toluene (23°C)
- ☺ iso-Octane (23°C)

Ketones

☺ Acetone (23°C)

Ethers

☺ Diethyl ether (23°C)

Mineral oils

☺ SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

- ☹ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ☹ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

Salt solutions

☹ Zinc Chloride solution (50% by mass) (23°C)

Other

- ☹ Ethylene Glycol (50% by mass) in water (108°C)
- ☺ 50% Oleic acid + 50% Olive Oil (23°C)
- ☹ Water (23°C)
- ☹ Deionized water (90°C)