


**TEREZ PA 6 7500 GF 30 FL HF /1**

PA6

Ter Plastics

**Product Texts**

Medium viscosity PA6, 30% glassfiber reinforced and halogen-free flame retardants.  
 For flame retarded moulding parts with high rigidity.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	9500	MPa	ISO 527-1/-2
Tensile Strength	100	MPa	ISO 527-1/-2
Yield stress	150	MPa	ISO 527-1/-2
Yield strain	2	%	ISO 527-1/-2
Strain at break	3	%	ISO 527-1/-2
Charpy impact strength (+23°C)	30	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	13	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load (1.80 MPa)	195	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Water absorption	6	%	Sim. to ISO 62
Humidity absorption	1.8	%	Sim. to ISO 62
Density	1440	kg/m <sup>3</sup>	ISO 1183

**Characteristics**
**Special Characteristics**

Flame retardant