


TEREZ PA 6 7111 K

PA6

Ter Plastics

Product Texts

Polyamid without release agent for injection moulding and extrusion.
 For all kind of moulding parts.

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Tensile Modulus | 3200 | MPa | ISO 527-1/-2 |
| Tensile Strength | 80 | MPa | ISO 527-1/-2 |
| Yield strain | 3 | % | ISO 527-1/-2 |
| Charpy impact strength (+23°C) | N | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength (+23°C) | 4 | kJ/m ² | ISO 179/1eA |
| Other properties | | | |
| ISO Data | | | |
| Density | 1130 | kg/m ³ | ISO 1183 |