

Technical information

TEREZ[®] PA 6 7750 T

Medium viscosity, dry impact resistant modified standard quality with good flow characteristics.



TECHNICAL DATA SHEET

Product text

For moulding parts with high impact stress.

Properties	Value	Unit	Test method
Density	1,1100	g/cm ³	ISO 1183
Impact strength Charpy (Notched 23°C), dry	12	kJ/m ²	ISO 179
Impact strength Charpy 23°C, dry	NB	kJ/m ²	ISO 179
Elongation at yield, dry	3,00	%	ISO 527
Yield strength, dry	75	MPa	ISO 527
Flexural modulus, dry	2100	MPa	ISO 178
Modulus in flexure, conditioned	900	MPa	ISO 178
Flexural strength, dry	100	MPa	ISO 178
Biegefestigkeit, konditioniert	35	MPa	ISO 178
Tensile-modulus, dry	2600	MPa	ISO 527
Tensile-modulus, conditioned	1100	MPa	ISO 527
Elongation at break, dry	50,00	%	ISO 527
Elongation at break, conditioned	60,00	%	ISO 527
Tensile strength, dry	65	MPa	ISO 527
Tensile strength, conditioned	34	MPa	ISO 527
HDT 0,45 MPa	165	°C	ISO 75
HDT 1,80 MPa	55	°C	ISO 75
CTI	600	V	IEC 60112
Volume resistivity, dry	1E13	Ohm * m	IEC 60093
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	1,6	mm	UL 94
UL recognition	-		UL 94
Water absorption	9,00	%	ISO 62
Moisture absorption	2,50	%	ISO 62

PROCESSING DATA SHEET

Processing guidelines for injection molding of TEREZ PA 6 7750 T

The processing data sheet provides guidelines about processing as well as pre-drying.

MATERIAL PREPARATION

Storage

Store in a dry place protected from direct sunlight. Avoid all sources of ignition like extreme heat, sparks, or open flame.

Drying

For the manufacturing of mechanically and optically optimal injection molding parts, we recommend following pre-drying conditions according to the table below. If the container is open (wet granules), the drying time can be extended accordingly.

Dry air dryer

Temperature	80°C
Time	4 - 8 hours
Due point	-40°C

Residual moisture

<= 0.05% (recommended)
max. 0.1% (standard)

MACHINE REQUIREMENTS

PROCESSING

Basic settings

The following basic settings are generally to be selected:

Processing temperatures

Hopper	60 - 80°C
Center	240 - 260°C
Nozzle	250 - 270°C

Mold temperature

Temp.	40 - 80°C
-------	-----------

Temperatures

Residence time

You should try to keep the residence time short, especially at high temperatures to avoid material degradation.

Residence times in the cylinder

max. 265 °C / 10 min.

Instructions for cleaning

The aggregate can be cleaned by using low MFI polypropylene. You can also use standard cleaning granulate.