





<b>Technyl® A 222</b>			
PA66		Solvay Engineering Plastics	
<b>Product Texts</b>			
Polyamide 6.6, unreinforced medium viscosity, for injection mouldin, heat stabilised nucleated for short cycle time			
<b>Mechanical properties</b>		<b>dry / cond</b>	<b>Unit</b>
<b>ISO Data</b>			
Tensile Modulus	3200 / 2000	MPa	ISO 527-1/-2
Stress at break	95 / -	MPa	ISO 527-1/-2
Strain at break	7 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / -	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>		<b>dry / cond</b>	<b>Unit</b>
<b>ISO Data</b>			
Melting temperature (10°C/min)	263 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	80 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	230 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	65 / *	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10
Oxygen index	26 / *	%	ISO 4589-1/-2
<b>Electrical properties</b>		<b>dry / cond</b>	<b>Unit</b>
<b>ISO Data</b>			
Relative permittivity, 100Hz	4.1 / 6	-	IEC 60250
Relative permittivity, 1MHz	2.9 / 3.2	-	IEC 60250
Dissipation factor, 100Hz	200 / 750	E-4	IEC 60250
Dissipation factor, 1MHz	290 / -	E-4	IEC 60250
Volume resistivity	>1E13 / 1E12	Ohm*m	IEC 60093
Surface resistivity	* / 1E13	Ohm	IEC 60093
Electric strength	27 / 26	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112
<b>Other properties</b>		<b>dry / cond</b>	<b>Unit</b>
<b>ISO Data</b>			
Water absorption	8.5 / *	%	Sim. to ISO 62
Humidity absorption	1.1 / *	%	Sim. to ISO 62
Density	1140 / -	kg/m <sup>3</sup>	ISO 1183
<b>Test specimen production</b>		<b>Value</b>	<b>Unit</b>
<b>ISO Data</b>			
Injection Molding, melt temperature	220	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 10724

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Stress-strain



Stress-strain



Characteristics

Processing

Injection Molding

Other text information

Injection Molding

PROCESSING

Melt temperature: 250°C

Mold temperature: 80°C

Chemical Media Resistance

Acids

- 😊 Acetic Acid (5% by mass) (23°C)
- 😊 Citric Acid solution (10% by mass) (23°C)
- 😊 Lactic Acid (10% by mass) (23°C)
- 🚫 Hydrochloric Acid (36% by mass) (23°C)
- 🚫 Nitric Acid (40% by mass) (23°C)
- 🚫 Sulfuric Acid (38% by mass) (23°C)
- 🚫 Sulfuric Acid (5% by mass) (23°C)
- 🚫 Chromic Acid solution (40% by mass) (23°C)

**Bases**

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

**Alcohols**

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)

**Hydrocarbons**

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)

**Ketones**

-  Acetone (23°C)

**Ethers**

-  Diethyl ether (23°C)

**Mineral oils**

-  SAE 10W40 multigrade motor oil (23°C)

**Standard Fuels**

-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

**Salt solutions**

-  Zinc Chloride solution (50% by mass) (23°C)

**Other**

-  Ethylene Glycol (50% by mass) in water (108°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)