





| Technyl® A 225F | | Solvay Engineering Plastics | |
|--|-------------------|-----------------------------|----------------------|
| PA66 | | | |
| Product Texts | | | |
| Polyamide 6.6, unreinforced medium viscosity, for injection moulding nucleated for short cycle time | | | |
| Mechanical properties | dry / cond | Unit | Test Standard |
| ISO Data | | | |
| Tensile Modulus | 3800 / 1600 | MPa | ISO 527-1/-2 |
| Stress at break | 95 / - | MPa | ISO 527-1/-2 |
| Strain at break | 20 / - | % | ISO 527-1/-2 |
| Charpy impact strength (+23°C) | N / - | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength (+23°C) | 4 / - | kJ/m ² | ISO 179/1eA |
| Thermal properties | | | |
| ISO Data | | | |
| Melting temperature (10°C/min) | 260 / * | °C | ISO 11357-1/-3 |
| Temp. of deflection under load (1.80 MPa) | 80 / * | °C | ISO 75-1/-2 |
| Temp. of deflection under load (0.45 MPa) | 220 / * | °C | ISO 75-1/-2 |
| Coeff. of linear therm. expansion, parallel | 65 / * | E-6/K | ISO 11359-1/-2 |
| Burning behav. at thickness h | V-2 / * | class | IEC 60695-11-10 |
| Thickness tested | 1.6 / * | mm | IEC 60695-11-10 |
| Electrical properties | | | |
| ISO Data | | | |
| Relative permittivity, 100Hz | 4.1 / 6 | - | IEC 60250 |
| Relative permittivity, 1MHz | 2.9 / 3.2 | - | IEC 60250 |
| Dissipation factor, 1MHz | 200 / - | E-4 | IEC 60250 |
| Volume resistivity | >1E13 / 1E12 | Ohm*m | IEC 60093 |
| Surface resistivity | * / 1E12 | Ohm | IEC 60093 |
| Electric strength | 27 / 26 | kV/mm | IEC 60243-1 |
| Comparative tracking index | 600 / - | - | IEC 60112 |
| Other properties | | | |
| ISO Data | | | |
| Density | 1140 / - | kg/m ³ | ISO 1183 |
| Test specimen production | | | |
| ISO Data | | | |
| Injection Molding, melt temperature | 220 | °C | ISO 294 |
| Injection Molding, mold temperature | 80 | °C | ISO 10724 |

Diagrams


Viscosity-shear rate



Shearstress-shear rate



Stress-strain



Characteristics

Processing

Injection Molding

Other text information

Injection Molding

PROCESSING

Melt temperature: 250°C

Mold temperature: 80°C

Chemical Media Resistance

Acids

- 😊 Acetic Acid (5% by mass) (23°C)
- 😊 Citric Acid solution (10% by mass) (23°C)
- 😊 Lactic Acid (10% by mass) (23°C)
- 🚫 Hydrochloric Acid (36% by mass) (23°C)
- 🚫 Nitric Acid (40% by mass) (23°C)
- 🚫 Sulfuric Acid (38% by mass) (23°C)
- 🚫 Sulfuric Acid (5% by mass) (23°C)
- 🚫 Chromic Acid solution (40% by mass) (23°C)

Bases

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)

Hydrocarbons

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)

Ketones

-  Acetone (23°C)

Ethers

-  Diethyl ether (23°C)

Mineral oils

-  SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

Salt solutions

-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethylene Glycol (50% by mass) in water (108°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)