


Technyl® A 230

PA66

Solvay Engineering Plastics

Product Texts

Polyamide 6.6 high fluidity, improved impact resistance, for injection moulding

Mechanical properties

dry / cond

Unit

Test Standard

ISO Data

Tensile Modulus

2200 / 1100

MPa

ISO 527-1/-2

Stress at break

52 / -

MPa

ISO 527-1/-2

Strain at break

40 / -

%

ISO 527-1/-2

Charpy impact strength (+23°C)

N / -

kJ/m²

ISO 179/1eU

Charpy notched impact strength (+23°C)

11 / -

kJ/m²

ISO 179/1eA

Thermal properties

dry / cond

Unit

Test Standard

ISO Data

Melting temperature (10°C/min)

258 / *

°C

ISO 11357-1/-3

Temp. of deflection under load (1.80 MPa)

85 / *

°C

ISO 75-1/-2

Coeff. of linear therm. expansion, parallel

70 / *

E-6/K

ISO 11359-1/-2

Burning behav. at thickness h

V-2 / *

class

IEC 60695-11-10

Thickness tested

1.6 / *

mm

IEC 60695-11-10

Oxygen index

21 / *

%

ISO 4589-1/-2

Electrical properties

dry / cond

Unit

Test Standard

ISO Data

Relative permittivity, 1MHz

3.3 / 4

-

IEC 60250

Dissipation factor, 1MHz

230 / -

E-4

IEC 60250

Volume resistivity

1E13 / 1E10

Ohm*m

IEC 60093

Surface resistivity

* / 1E13

Ohm

IEC 60093

Electric strength

30 / 28

kV/mm

IEC 60243-1

Comparative tracking index

600 / -

-

IEC 60112

Other properties

dry / cond

Unit

Test Standard

ISO Data

Density

1090 / -

kg/m³

ISO 1183

Test specimen production

Value

Unit

Test Standard

ISO Data

Injection Molding, melt temperature

220

°C

ISO 294

Injection Molding, mold temperature


80

°C

ISO 10724

Diagrams

Stress-strain



Characteristics

Processing

Injection Molding

Other text information

Injection Molding

PROCESSING

Melt temperature: 255°C

Mold temperature: 80°C

Chemical Media Resistance

Acids

- ☺ Acetic Acid (5% by mass) (23°C)
- ☺ Citric Acid solution (10% by mass) (23°C)
- ☺ Lactic Acid (10% by mass) (23°C)
- ☹ Hydrochloric Acid (36% by mass) (23°C)
- ☹ Nitric Acid (40% by mass) (23°C)
- ☹ Sulfuric Acid (38% by mass) (23°C)
- ☹ Sulfuric Acid (5% by mass) (23°C)
- ☹ Chromic Acid solution (40% by mass) (23°C)

Bases

- ☹ Sodium Hydroxide solution (35% by mass) (23°C)
- ☺ Sodium Hydroxide solution (1% by mass) (23°C)
- ☺ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ☹ Isopropyl alcohol (23°C)
- ☹ Methanol (23°C)
- ☹ Ethanol (23°C)

Hydrocarbons

- ☺ n-Hexane (23°C)
- ☺ Toluene (23°C)
- ☺ iso-Octane (23°C)

Ketones

 Acetone (23°C)

Ethers

 Diethyl ether (23°C)

Mineral oils

 SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

 Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)

 Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

Salt solutions

 Zinc Chloride solution (50% by mass) (23°C)

Other

 Ethylene Glycol (50% by mass) in water (108°C)

 50% Oleic acid + 50% Olive Oil (23°C)

 Water (23°C)

 Deionized water (90°C)