


TEREZ PA 6.6 7111/1 R

PA66

Ter Plastics

Product Texts

PA66 standard type with medium viscosity
 For all kind of injection molding parts

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3600	MPa	ISO 527-1/-2
Tensile Strength	85	MPa	ISO 527-1/-2
Strain at break	20	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	80	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	190	°C	ISO 75-1/-2
Other properties			
ISO Data			
Water absorption	8.6	%	Sim. to ISO 62
Humidity absorption	2.4	%	Sim. to ISO 62
Density	1140	kg/m ³	ISO 1183