



Stanyl® 46HF5041LW			
PA46-GF40 FR(17)		DSM Engineering Plastics	
Product Texts			
40% Glass Reinforced, Heat Stabilized, Flame Retardant, High Flow, Low Warpage			
ISO 1043 PA46-GF40 FR(17)			
Mechanical properties			
	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	16000 / 12000	MPa	ISO 527-1/-2
Stress at break	150 / 100	MPa	ISO 527-1/-2
Strain at break	1.3 / 2	%	ISO 527-1/-2
Charpy impact strength (+23°C)	25 / 35	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	25 / 25	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	7 / 7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	7 / 7	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	270 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	290 / *	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	290 / *	°C	ISO 306
Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	40 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	UL / *	-	-
Burning behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
UL recognition	UL / *	-	-
Electrical properties			
	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	4.3 / -	-	IEC 60250
Relative permittivity, 1MHz	4 / -	-	IEC 60250
Dissipation factor, 100Hz	60 / -	E-4	IEC 60250
Dissipation factor, 1MHz	160 / -	E-4	IEC 60250
Volume resistivity	>1E13 / 1E8	Ohm*m	IEC 60093
Surface resistivity	* / 1E14	Ohm	IEC 60093
Electric strength	30 / 20	kV/mm	IEC 60243-1
Comparative tracking index	300 / -	-	IEC 60112
Other properties			
	dry / cond	Unit	Test Standard
ISO Data			
Water absorption	4.3 / *	%	Sim. to ISO 62
Humidity absorption	1.2 / *	%	Sim. to ISO 62
Density	1870 / -	kg/m ³	ISO 1183
Material specific properties			
	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	70 / *	cm ³ /g	ISO 307, 1157, 1628

Stanyl® 46HF5041LW

PA46-GF40 FR(17)

DSM Engineering Plastics

Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Density of melt	1650	kg/m ³	-
Thermal conductivity of melt	0.252	W/(m K)	-
Spec. heat capacity of melt	1520	J/(kg K)	-
Eff. thermal diffusivity	1.02E-7	m ² /s	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant, Platable, Heat stabilized or stable to heat

Additives

Lubricants, Release agent

Other text information**Injection Molding**[Injection Molding Recommendations](#)