

TECHNICAL DATA SHEET

Stanyl® TE200F6

Envalior
PA46-GF30

Processing

Injection molding

Delivery Form

Pellets

Special Characteristics

Platable, Heat stabilized or stable to heat

Features

Low warpage

Product Text

Product Information

30% Glass Reinforced, Heat Stabilized

ISO 1043 PA46-GF30

Stanyl® TE200F6 is an electro-friendly high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

Processing/Physical Characteristics	Value	Unit	Standard
Density of melt	1280	kg/m ³	
Thermal conductivity of melt	0.28	W/(m K)	
Spec. heat capacity of melt	2430	J/(kg K)	
Eff. thermal diffusivity	9.02E-8	m ² /s	
Mechanical Properties	Value	Unit	Standard
Tensile modulus	10000	MPa	ISO 527
Stress at break	210	MPa	ISO 527
Strain at break	3.7	%	ISO 527
Poisson's ratio	0.35		ISO 527
Tensile creep modulus, 1000h	4500	MPa	ISO 899-1
Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	65	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	11	kJ/m ²	ISO 179/1eA

Stanyl® TE200F6

Envalior


Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	295	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	75	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	290	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	290	°C	ISO 75-1/-2
Vicat softening temperature, B	290	°C	ISO 306
Coeff. of linear therm. expansion, parallel	25	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	60	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	
Yellow card available	yes		
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3	mm	
Yellow card available	yes		
Oxygen index	22	%	ISO 4589-1/-2
Electrical Properties	Value	Unit	Standard
Relative permittivity, 100Hz	4.4		IEC 62631-2-1
Relative permittivity, 1MHz	4		IEC 62631-2-1
Dissipation factor, 100Hz	80	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	230	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Electric strength	35	kV/mm	IEC 60243-1
Comparative tracking index	500		IEC 60112
Other Properties	Value	Unit	Standard
Water absorption	9.5	%	Sim. to ISO 62
Humidity absorption	2.6	%	Sim. to ISO 62
Density	1410	kg/m ³	ISO 1183
Material Specific Properties	Value	Unit	Standard
Viscosity number	145	cm ³ /g	ISO 307, 1157, 1628

Diagrams


Stanyl® TE200F6

Envalior


Stress-strain




Stress-strain



True stress-true strain




True stress-true strain




Stanyl® TE200F6

Envalior


Secant modulus-strain




Secant modulus-strain



Viscosity-shear rate




Shearstress-shear rate




Stanyl® TE200F6

Envalior


Dynamic shear modulus-temperature




Stress-strain (isochronous) 23°C



Creep modulus-time 23°C




Creep curve 23°C




Stanyl® TE200F6

Envalior


Stress-strain (isochronous) 100°C




Creep modulus-time 100°C



Creep curve 100°C




Stress-strain (isochronous) 140°C




Stanyl® TE200F6

Envalior


Creep modulus-time 140°C




Creep curve 140°C



Stress-strain (isochronous) 160°C




Creep modulus-time 160°C




Stanyl® TE200F6

Envalior

Creep curve 160°C



LTHA-strain at break



Processing Information

Injection molding

Injection Molding Recommendations

Hot runner recommendations for molding high heat performance Engineering Materials

Steel recommendations for molds screws and barrels

Supporting document for Stanyl quality processing

Trouble shooting guideline for injection molding