

Technical information

TEREZ[®] PA 6.6 7750 T GF 30

Dry impact resistant Polyamide 6.6, 30% glass fibre reinforced.



TECHNICAL DATA SHEET

Product text

For all kind of moulded parts, with high impact properties and stiffness.

Properties	Value	Unit	Test method
Density	1,3200	g/cm ³	ISO 1183
Impact strength Charpy (Notched 23°C), dry	12	kJ/m ²	ISO 179
Impact strength Charpy (Notched 23°), conditioned	17	kJ/m ²	ISO 179
Impact strength Charpy 23°C, dry	60	kJ/m ²	ISO 179
Impact strength Charpy (23°), conditioned	70	kJ/m ²	ISO 179
Tensile-modulus, dry	8100	MPa	ISO 527
Tensile-modulus, conditioned	6200	MPa	ISO 527
Tensile stress at break, dry	140	MPa	ISO 527
Tensile stress at break, conditioned	100	MPa	ISO 527
Elongation at break, dry	3,00	%	ISO 527
Elongation at break, conditioned	6,00	%	ISO 527
HDT 0,45 MPa	240	°C	ISO 75
HDT 1,80 MPa	230	°C	ISO 75
CTI	550	V	IEC 60112
Volume resistivity, dry	1E14	Ohm * m	IEC 60093
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	1,6	mm	UL 94
UL recognition	-		UL 94
GWFI at 1,0 mm	650	°C	IEC 60695-2-12
Water absorption	5,40	%	ISO 62
Moisture absorption	1,50	%	ISO 62

PROCESSING DATA SHEET

Processing guidelines for injection molding of TEREZ PA 6.6 7750 T GF 30

The processing data sheet provides guidelines about processing as well as pre-drying.

MATERIAL PREPARATION

Storage

Store in a dry place protected from direct sunlight. Avoid all sources of ignition like extreme heat, sparks, or open flame.

Drying

For the manufacturing of mechanically and optically optimal injection molding parts, we recommend following pre-drying conditions according to the table below. If the container is open (wet granules), the drying time can be extended accordingly.

Dry air dryer

Temperature	80°C
Time	4 - 8 hours
Due point	-40°C

Residual moisture

<= 0.05% (recommended)
max. 0.1% (standard)

MACHINE REQUIREMENTS

PROCESSING

Basic settings

The following basic settings are generally to be selected:

Processing temperatures

Hopper	60 - 80°C
Center	260 - 290°C
Nozzle	270 - 300°C

Mold temperature

Temp.	40 - 80°C
-------	-----------

Temperatures

Residence time

You should try to keep the residence time short, especially at high temperatures to avoid material degradation.

Residence times in the cylinder

max. 280 °C / 8 min.

Instructions for cleaning

The aggregate can be cleaned by using low MFI polypropylene. You can also use standard cleaning granulate.