


**Technyl® eXten D 218 V30**

PA610-GF30

Solvay Engineering Plastics


**Product Texts**
Technyl® eXten D 218 V30 is a 30% Glass Fibre reinforced and heat stabilized product suitable to the

manufacturing of all injection moulded parts.


<b>Rheological properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5 / *	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	8500 / 6100	MPa	ISO 527-1/-2
Stress at break	152 / 112	MPa	ISO 527-1/-2
Strain at break	4.5 / 7.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	90 / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	85 / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 17	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	10 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature (10°C/min)	215 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	195 / *	°C	ISO 75-1/-2
Thickness tested	1.6 / *	mm	IEC 60695-11-10
UL recognition	UL / *	-	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
<b>Other properties</b>			
<b>ISO Data</b>			
Water absorption	2.1 / *	%	Sim. to ISO 62
Humidity absorption	0.33 / *	%	Sim. to ISO 62
Density	1300 / -	kg/m <sup>3</sup>	ISO 1183

Diagrams


Stress-strain




Stress-strain



Secant modulus-strain



Secant modulus-strain



Other text information

Injection Molding

The material is supplied in weight bags, ready for use. In the case that the virgin material has absorbed moisture, it must be dried to a final moisture content less than 0.2% with a dehumidified air drying equipment at approximately 80°C.

Recommended moulding conditions:

- Barrel temperatures
- Feed zone

Chemical Media Resistance

Acids

- 😊 Acetic Acid (5% by mass) (23°C)
- 🚫 Sulfuric Acid (38% by mass) (23°C)
- 🚫 Sulfuric Acid (5% by mass) (23°C)

Alcohols

 Ethanol (23°C)

**Hydrocarbons**

 Toluene (23°C)

**Ketones**

 Acetone (23°C)

**Mineral oils**

 SAE 10W40 multigrade motor oil (23°C)

**Standard Fuels**

 Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

**Salt solutions**

 Zinc Chloride solution (50% by mass) (23°C)

**Other**

-  Hydrogen peroxide (23°C)
-  Ethylene Glycol (50% by mass) in water (108°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Deionized water (90°C)
-  Phenol solution (5% by mass) (23°C)