


TEREZ PA 6.6 7750 TC

PA66

Ter Plastics

Product Texts

Dry impact unfilled Polyamide 6.6, good flowability and demoulding properties.
 For all kind of moulding parts with high impact resistance.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3100	MPa	ISO 527-1/-2
Tensile Strength	64	MPa	ISO 527-1/-2
Yield stress	75	MPa	ISO 527-1/-2
Yield strain	6	%	ISO 527-1/-2
Stress at break	22	MPa	ISO 527-1/-2
Strain at break	7	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	9	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	75	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	185	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
Electrical properties			
ISO Data			
Comparative tracking index	550	-	IEC 60112
Other properties			
ISO Data			
Water absorption	7	%	Sim. to ISO 62
Humidity absorption	2.5	%	Sim. to ISO 62
Density	1160	kg/m ³	ISO 1183