

TECHNICAL DATA SHEET

# Stanyl® TE250F8

Envalior  
PA46-GF40 FR(17)

**Processing**

Injection molding

**Delivery Form**

Pellets

**Additives**

Lubricants, Release agent

**Special Characteristics**

Flame retardant, Platable, Heat stabilized or stable to heat

## Product Text

**Product Information**

40% Glass Reinforced, Heat Stabilized, Flame Retardant

ISO 1043 PA46-GF40 FR(17)

Processing/Physical Characteristics	Value	Unit	Standard
Density of melt	1570	kg/m <sup>3</sup>	
Thermal conductivity of melt	0.353	W/(m K)	
Spec. heat capacity of melt	1630	J/(kg K)	
Eff. thermal diffusivity	1.41E-7	m <sup>2</sup> /s	
Mechanical Properties	Value	Unit	Standard
Tensile modulus	16000	MPa	ISO 527
Stress at break	190	MPa	ISO 527
Strain at break	1.9	%	ISO 527
Poisson's ratio	0.35		ISO 527
Charpy impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	13	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	13	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	295	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	75	°C	ISO 11357-1/-2

# Stanyl® TE250F8

Envalior


Thermal Properties	Value	Unit	Standard
Temp. of deflection under load, 1.80 MPa	290	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	290	°C	ISO 75-1/-2
Vicat softening temperature, B	290	°C	ISO 306
Coeff. of linear therm. expansion, parallel	25	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	50	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	
Yellow card available	yes		
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3	mm	
Yellow card available	yes		
Oxygen index	37	%	ISO 4589-1/-2
Electrical Properties	Value	Unit	Standard
Relative permittivity, 100Hz	4.3		IEC 62631-2-1
Relative permittivity, 1MHz	4		IEC 62631-2-1
Dissipation factor, 100Hz	60	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	160	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	325		IEC 60112
Other Properties	Value	Unit	Standard
Water absorption	4.6	%	Sim. to ISO 62
Humidity absorption	1.3	%	Sim. to ISO 62
Density	1760	kg/m <sup>3</sup>	ISO 1183
Material Specific Properties	Value	Unit	Standard
Viscosity number	150	cm <sup>3</sup> /g	ISO 307, 1157, 1628

## Diagrams


# Stanyl® TE250F8

Envalior


Stress-strain




Stress-strain



True stress-true strain




True stress-true strain




# Stanyl® TE250F8

Envalior


Secant modulus-strain




Secant modulus-strain



Viscosity-shear rate




Shearstress-shear rate




# Stanyl® TE250F8

Envalior


Spec. volume-Temperature (pVT)




Dynamic shear modulus-temperature



LTHA-stress at break



LTHA-strain at break



## Processing Information

### Injection molding

#### Injection Molding Recommendations

Hot runner recommendations for molding high heat performance Engineering Materials

Steel recommendations for molds screws and barrels

Supporting document for Stanyl quality processing

Trouble shooting guideline for injection molding