

**TECHNICAL DATA SHEET**

# Stanyl® TE250F9

Envalior  
PA46-GF45 FR(17)

**Processing**

Injection molding

**Delivery Form**

Pellets

**Additives**

Lubricants, Release agent

**Special Characteristics**

Flame retardant, Platable, Heat stabilized or stable to heat

## Product Text

**Product Information**

45% Glass Reinforced, Heat Stabilized, Flame Retardant

ISO 1043 PA46-GF45 FR(17)

Stanyl® TE250F9 is an electro-friendly & flame-retarded high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

Processing/Physical Characteristics	Value	Unit	Standard
Density of melt	1710	kg/m <sup>3</sup>	
Thermal conductivity of melt	0.344	W/(m K)	
Spec. heat capacity of melt	1530	J/(kg K)	
Eff. thermal diffusivity	1.42E-7	m <sup>2</sup> /s	
Mechanical Properties	Value	Unit	Standard
Tensile modulus	17000	MPa	ISO 527
Stress at break	200	MPa	ISO 527
Strain at break	2.2	%	ISO 527
Poisson's ratio	0.35		ISO 527
Tensile creep modulus, 1000h	12000	MPa	ISO 899-1
Charpy impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	14	kJ/m <sup>2</sup>	ISO 179/1eA

# Stanyl® TE250F9


Envalior

Mechanical Properties	Value	Unit	Standard
Charpy notched impact strength, -30°C	13	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	295	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	75	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	290	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	290	°C	ISO 75-1/-2
Vicat softening temperature, B	290	°C	ISO 306
Coeff. of linear therm. expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	45	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	
Yellow card available	yes		
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3	mm	
Yellow card available	yes		
Oxygen index	37	%	ISO 4589-1/-2
Electrical Properties	Value	Unit	Standard
Relative permittivity, 100Hz	4.3		IEC 62631-2-1
Relative permittivity, 1MHz	4		IEC 62631-2-1
Dissipation factor, 100Hz	60	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	160	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	250		IEC 60112
Other Properties	Value	Unit	Standard
Water absorption	4.8	%	Sim. to ISO 62
Humidity absorption	1.2	%	Sim. to ISO 62
Density	1820	kg/m <sup>3</sup>	ISO 1183
Material Specific Properties	Value	Unit	Standard
Viscosity number	140	cm <sup>3</sup> /g	ISO 307, 1157, 1628


# Stanyl® TE250F9

Envalior


Stress-strain




Stress-strain



True stress-true strain




True stress-true strain




# Stanyl® TE250F9

Envalior


Secant modulus-strain




Secant modulus-strain



Viscosity-shear rate





Shearstress-shear rate



# Stanyl® TE250F9

Envalior



## Processing Information

### Injection molding

#### Injection Molding Recommendations

Hot runner recommendations for molding high heat performance Engineering Materials

Steel recommendations for molds screws and barrels

Supporting document for Stanyl quality processing

Trouble shooting guideline for injection molding