## Arnite® T06 204 SN
PBT FR(17)   DSM Engineering Plastics

Product Texts
Flame Retardant, High Flow

ISO 1043 PBT FR(17)

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	41	cm³/10min	ISO 1133
Temperature	250	°C	ISO 1133
Load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3200	MPa	ISO 527-1/-2
Yield stress	65	MPa	ISO 527-1/-2
Yield strain	5	%	ISO 527-1/-2
Nominal strain at break	5.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5	kJ/m²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	75	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	165	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	90	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	90	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	IEC 60695-11-10
UL recognition	UL	-	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	IEC 60695-11-10
UL recognition	UL	-	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 60093
Comparative tracking index	225	-	IEC 60112

Other properties	Value	Unit	Test Standard
ISO Data			
Water absorption	0.45	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62
Density	1440	kg/m³	ISO 1183

Arnite® T06 204 SN
PBT FR(17)   DSM Engineering Plastics

Diagrams

Stress-strain

Stress-strain
Arnite® T06 204 SN

Secant modulus-strain

Secant modulus-strain
Arnite® T06 204 SN

Characteristics

Processing	Additives
Injection Molding	Release agent

Delivery form	Special Characteristics
Pellets	Flame retardant

Other text information

Injection Molding
Injection Molding Recommendations