

TECHNICAL DATA SHEET

PBT-4120

ChangChun Group

PBT-GF20

Delivery Form

Pellets

Special Characteristics

Flame retardant

Processing/Physical Characteristics	Value	Unit	Standard
Mold shrinkage, MD	0.0045	mm/mm	ASTM D 955
Mold shrinkage, TD	0.015	mm/mm	ASTM D 955
Mechanical Properties	Value	Unit	Standard
Tensile strength	103	MPa	ASTM D 638
Flexural modulus	4905	MPa	ASTM D 790
Flexural strength	142	MPa	ASTM D 790
Rockwell hardness	M 93		ASTM D 785
Izod impact notched, 1/4 in	75.42	J/m	ASTM D 256
Thermal Properties	Value	Unit	Standard
UL 94 flame rating	V-0		UL 94
Thickness tested	0.8	mm	
Coefficient of thermal expansion, MD	35	E-6/K	ASTM D 696
DTUL @ 66 psi	220	°C	ASTM D 648
DTUL @ 264 psi	205	°C	ASTM D 648
Melting temperature	225	°C	ASTM D 3418
Electrical Properties	Value	Unit	Standard
Dielectric strength, short time	20	kV/mm	ASTM D 149
Dissipation factor, 60 Hz	0.001		ASTM D 150
Dielectric constant, 60 Hz	3.5		ASTM D 150
Surface resistivity	1E13	Ohm	ASTM D 257
Volume resistivity	>1E15	Ohm*cm	ASTM D 257
Arc resistance	90	s	ASTM D 495

PBT-4120

ChangChun Group

Other Properties	Value	Unit	Standard
Water absorption, 24hr	0.03	%	ASTM D 570
Density	1570	kg/m³	ASTM D 792