

## TECHNICAL DATA SHEET

# PBT 2000-201D

ChangChun Group

PBT

**Processing**

Injection molding

**Chemical Resistance**

Solvent resistance, Oil resistance

**Special Characteristics**

 U.V. stabilized or stable to weather, Heat stabilized or stable to heat  
 Electrical and electronical

**Applications**

Processing/Physical Characteristics	Value	Unit	Standard
Mold shrinkage, MD	0.0135	mm/mm	ASTM D 955
Mold shrinkage, TD	0.0165	mm/mm	ASTM D 955
Mechanical Properties	Value	Unit	Standard
Tensile strength	58.9	MPa	ASTM D 638
Flexural modulus	2453	MPa	ASTM D 790
Flexural strength	98.1	MPa	ASTM D 790
Rockwell hardness	M 80		ASTM D 785
Izod impact notched, 1/4 in	28.28	J/m	ASTM D 256
Thermal Properties	Value	Unit	Standard
UL 94 flame rating	V-0		UL 94
Thickness tested	0.8	mm	
Coefficient of thermal expansion, MD	90	E-6/K	ASTM D 696
DTUL @ 66 psi	165	°C	ASTM D 648
DTUL @ 264 psi	65	°C	ASTM D 648
Melting temperature	225	°C	ASTM D 3418
Electrical Properties	Value	Unit	Standard
Dielectric strength, short time	20	kV/mm	ASTM D 149
Dissipation factor, 60 Hz	0.001		ASTM D 150
Dielectric constant, 60 Hz	3.3		ASTM D 150
Surface resistivity	1E13	Ohm	ASTM D 257
Volume resistivity	1E15	Ohm*cm	ASTM D 257

# PBT 2000-201D

ChangChun Group

Electrical Properties	Value	Unit	Standard
Arc resistance	100	s	ASTM D 495

  

Other Properties	Value	Unit	Standard
Water absorption, 24hr	0.05	%	ASTM D 570
Density	1440	kg/m <sup>3</sup>	ASTM D 792