


TEREZ PC/ABS Blend 1000

(PC+ABS)

Ter Plastics

Product Texts

Heat resistant, high impact strength (notched) minor inclination of brittle fracture.
 All kind of Injection moulding parts.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	30	g/10min	ISO 1133
MFI temperature	250	°C	ISO 1133
MFI load	5	kg	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	2300	MPa	ISO 527-1/-2
Stress at break	40	MPa	ISO 527-1/-2
Strain at break	50	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	40	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	95	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	110	°C	ISO 306
Other properties			
ISO Data			
Density	1120	kg/m ³	ISO 1183