


TEREZ PC/ABS Blend 2000 UV

(ABS+PC)

Ter Plastics

Product Texts

PC/ABS Blend with good heat resistant, high impact strength, low inclination to brittle failure and UV resistant.
 For all kind of injection moulding parts.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	33	g/10min	ISO 1133
MFI temperature	250	°C	ISO 1133
MFI load	5	kg	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	2800	MPa	ISO 527-1/-2
Tensile Strength	55	MPa	ISO 527-1/-2
Yield stress	60	MPa	ISO 527-1/-2
Yield strain	5	%	ISO 527-1/-2
Strain at break	50	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	60	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load (1.80 MPa)	105	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	120	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
Other properties			
ISO Data			
Water absorption	0.6	%	Sim. to ISO 62
Density	1120	kg/m ³	ISO 1183

Characteristics
Special Characteristics

Light stabilized or stable to light