

TECHNICAL DATA SHEET

XANTAR™ LDS 3734

Mitsubishi EP
PC FR

Processing

Injection molding

Delivery Form

Pellets

Additives

Release agent

Special Characteristics

Flame retardant, Platable

Product Text

Product Information

Laser Direct Structuring (LDS) *, Flame Retardant (Halogen free), Impact Modified

ISO 1043 PC FR

XANTAR Polycarbonate & Blends, your global partner for innovative added value

**The compound is intended specifically for the use in the process of manufacturing conducting path designs according to the German application of the patent 101 32 092 of LPKF Laser & Electronics AG (Osteriede 7 30827 Garbsen Germany). Please address straight to LPKF Laser & Electronics AG (www.LPKF.de).*

Processing/Physical Characteristics	Value	Unit	Standard
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Mechanical Properties	Value	Unit	Standard
Tensile modulus	2200	MPa	ISO 527
Yield stress	50	MPa	ISO 527
Yield strain	6	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Poisson's ratio	0.35		ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	45	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	25	kJ/m ²	ISO 179/1eA
Puncture energy, +23°C	40	J	ISO 6603-2

XANTAR™ LDS 3734

Mitsubishi EP

Thermal Properties	Value	Unit	Standard
Temp. of deflection under load, 1.80 MPa	120	°C	ISO 75-1/-2
Vicat softening temperature, B	142	°C	ISO 306
Coeff. of linear therm. expansion, parallel	60	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	60	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.4	mm	

Electrical Properties	Value	Unit	Standard
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2

Other Properties	Value	Unit	Standard
Water absorption	0.35	%	Sim. to ISO 62
Density	1290	kg/m ³	ISO 1183




Test Specimen Production	Value	Unit	Standard
Injection molding, melt temperature	290	°C	ISO 294
Injection molding, mold temperature	100	°C	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Standard
Pre-drying - temperature	100 - 120	°C	
Pre-drying - time	4 - 6	h	
Processing humidity	≤0.03	%	
Melt temperature	270 - 300	°C	
Mold temperature	80 - 120	°C	
Zone 1	260 - 280	°C	
Zone 2	270 - 290	°C	
Zone 3	270 - 300	°C	
Nozzle temperature	270 - 290	°C	

Diagrams

XANTAR™ LDS 3734

Mitsubishi EP



Processing Information

XANTAR™ LDS 3734

Mitsubishi EP

Injection molding

Injection Molding Recommendations