

TECHNICAL DATA SHEET

# DURACON® CH-20

Polyplastics  
POM-CF20

**Special Characteristics**

Increased electrical conductivity

Processing/Physical Characteristics	Value	Unit	Standard
Melt volume-flow rate, MVR	2	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Melt flow index, MFI	2.5	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577
Mechanical Properties	Value	Unit	Standard
Tensile modulus	14000	MPa	ISO 527
Tensile strength	144	MPa	ISO 527
Strain at break	1.5	%	ISO 527
Poisson's ratio	0.35		ISO 527
Flexural modulus, 23°C	12000	MPa	ISO 178
Flexural strength	205	MPa	ISO 178
Charpy notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	M 95		ISO 2039-2
Thermal Properties	Value	Unit	Standard
Temp. of deflection under load, 1.80 MPa	163	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	10	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	80	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Yellow card available	yes		

# DURACON® CH-20

Polyplastics

Other Properties	Value	Unit	Standard
Density	1470	kg/m <sup>3</sup>	ISO 1183