



Tarnoform® 210			
POM		Grupa Azoty S.A.	
Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	2.2	cm ³ /10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Melt flow index, MFI	2.5	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527-1/-2
Yield stress	59	MPa	ISO 527-1/-2
Yield strain	13	%	ISO 527-1/-2
Strain at break	40	%	ISO 527-1/-2
Charpy impact strength (+23°C)	260	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8.5	kJ/m ²	ISO 179/1eA
Flexural modulus (23°C)	2200	MPa	ISO 178
Izod Impact notched, 23°C	8	kJ/m ²	ISO 180/1A
Ball indentation hardness	140	MPa	ISO 2039-1
Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature (10°C/min)	167	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	105	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	145	°C	ISO 306
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	IEC 60695-11-10
Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.8	-	IEC 60250
Volume resistivity	1E13	Ohm*m	IEC 60093
Surface resistivity	1E14	Ohm	IEC 60093
Electric strength	25	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
Other properties	Value	Unit	Test Standard
ISO Data			
Water absorption	0.8	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1400	kg/m ³	ISO 1183
Characteristics			
Processing		Features	
Injection Molding, Sheet Extrusion, Other Extrusion, Blow Molding, Pipe/Tube Extrusion		Thermal Stability, Copolymer	

Tarnoform® 210

POM

Grupa Azoty S.A.

Delivery form

Granules, Black, Natural Color