



Tarnoform® 300 M			
POM		Grupa Azoty S.A.	
Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	7.5	cm ³ /10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Melt flow index, MFI	8.5	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2700	MPa	ISO 527-1/-2
Yield stress	62	MPa	ISO 527-1/-2
Yield strain	9.5	%	ISO 527-1/-2
Strain at break	25	%	ISO 527-1/-2
Charpy impact strength (+23°C)	90	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5	kJ/m ²	ISO 179/1eA
Flexural modulus (23°C)	2500	MPa	ISO 178
Izod Impact notched, 23°C	6	kJ/m ²	ISO 180/1A
Ball indentation hardness	155	MPa	ISO 2039-1
Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature (10°C/min)	167	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	115	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	150	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	IEC 60695-11-10
Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	4.1	-	IEC 60250
Dissipation factor, 1MHz	100	E-4	IEC 60250
Volume resistivity	1E12	Ohm*m	IEC 60093
Surface resistivity	1E14	Ohm	IEC 60093
Electric strength	25	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
Other properties	Value	Unit	Test Standard
ISO Data			
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1420	kg/m ³	ISO 1183
Characteristics			
Processing	Features		
Injection Molding	Low Coefficient of Friction, Copolymer		
Delivery form			
Granules, Black, Natural Color			