



<b>Tarnoform® 300 WD</b>			
POM		Grupa Azoty S.A.	
<b>Rheological properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	8	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Melt flow index, MFI	9	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	2700	MPa	ISO 527-1/-2
Yield stress	60	MPa	ISO 527-1/-2
Yield strain	9	%	ISO 527-1/-2
Strain at break	40	%	ISO 527-1/-2
Charpy impact strength (+23°C)	180	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	6	kJ/m <sup>2</sup>	ISO 179/1eA
Flexural modulus (23°C)	2300	MPa	ISO 178
Izod Impact notched, 23°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Ball indentation hardness	145	MPa	ISO 2039-1
<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature (10°C/min)	167	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	110	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	145	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	IEC 60695-11-10
<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1410	kg/m <sup>3</sup>	ISO 1183
<b>Characteristics</b>			
<b>Processing</b>	<b>Features</b>		
Injection Molding	Copolymer		
<b>Delivery form</b>			
Granules, Black, Natural Color			