



TEREZ POM 8007			
POM		Ter Plastics	
Product Texts			
Standard grade, good flowability. (reduced Plate out) Moulding parts of all kind, nuts and screws, bearing and clutch-parts, pump elements.			
Rheological properties		Value	Unit
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
Mechanical properties		Value	Unit
ISO Data			
Tensile Modulus	2800	MPa	ISO 527-1/-2
Tensile Strength	62	MPa	ISO 527-1/-2
Yield strain	10	%	ISO 527-1/-2
Strain at break	25	%	ISO 527-1/-2
Charpy impact strength (+23°C)	170	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6	kJ/m ²	ISO 179/1eA
Thermal properties		Value	Unit
ISO Data			
Temp. of deflection under load (1.80 MPa)	115	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	150	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
Other properties		Value	Unit
ISO Data			
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1410	kg/m ³	ISO 1183