



Tarnoform® 411 K			
POM			Grupa Azoty S.A.
Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
MFI temperature	190	°C	ISO 1133
MFI load	2.16	kg	ISO 1133
Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	58	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	3.5	kJ/m ²	ISO 179/1eA
Ball indentation hardness	150	MPa	ISO 2039-1
Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature (10°C/min)	167	°C	ISO 11357-1/-3
Characteristics			
Processing		Features	
Injection Molding		Low Coefficient of Friction, Copolymer	
Delivery form			
Granules			