

TECHNICAL DATA SHEET

DURAFIDE® 6565A6

Polyplastics
PPS-(GF+MD)65

Features

Good adhesion

Mechanical Properties	Value	Unit	Standard
Tensile strength	125	MPa	ISO 527
Strain at break	1	%	ISO 527
Flexural modulus, 23°C	21000	MPa	ISO 178
Flexural strength	185	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Rockwell hardness	M 95		ISO 2039-2
Thermal Properties	Value	Unit	Standard
Temp. of deflection under load, 1.80 MPa	275	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	10	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	30	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Yellow card available	yes		
Electrical Properties	Value	Unit	Standard
Relative permittivity, 1MHz	5.4		IEC 62631-2-1
Dissipation factor, 1MHz	50	E-4	IEC 62631-2-1
Volume resistivity	2E14	Ohm*m	IEC 62631-3-1
Electric strength	16	kV/mm	IEC 60243-1
Comparative tracking index	225		IEC 60112
Arc resistance	189	s	ASTM D 495
Other Properties	Value	Unit	Standard
Density	1960	kg/m ³	ISO 1183