

TECHNICAL DATA SHEET

Gryfilen® H12-AGF

Grupa Azoty S.A.

PP

Processing

Other extrusion

Features

Gas fading resistance, Homopolymer

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	
Load	2.16	kg	

Mechanical Properties	Value	Unit	Standard
Yield stress	37	MPa	ISO 527
Yield strain	7	%	ISO 527
Flexural modulus, 23°C	1600	MPa	ISO 178
Izod notched impact strength, +23°C	2.7	kJ/m ²	ISO 180/1A