

TECHNICAL DATA SHEET

TERmicron PP H 905 25 / 08

TEREZ PERFORMANCE POLYMERS

PP

Processing

Injection molding, Fiber extrusion, Other extrusion

Delivery Form

Powder

Features

Gas fading resistance, Homopolymer

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	
Load	2.16	kg	
Mechanical Properties	Value	Unit	Standard
Tensile modulus	1600	MPa	ISO 527
Yield stress	32	MPa	ISO 527
Yield strain	9	%	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A
Rockwell hardness	R 95		ISO 2039-2
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, A	153	°C	ISO 306
Vicat softening temperature, B	89	°C	ISO 306
Other Properties	Value	Unit	Standard
Density	905	kg/m ³	ISO 1183
Bulk density	525	kg/m ³	