

TECHNICAL DATA SHEET

TOTAL 10641

TotalEnergies

Processing

Injection molding

Special Characteristics

Anti-static

Features

Nucleated, Copolymer

Certifications

Food contact

Applications

Packaging

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	44	g/10min	ISO 1133
Temperature	230	°C	
Load	2.16	kg	
Mechanical Properties	Value	Unit	Standard
Tensile modulus	1600	MPa	ISO 527
Yield stress	27	MPa	ISO 527
Yield strain	4	%	ISO 527
Poisson's ratio	0.35		ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m²	ISO 179/1eA
Izod notched impact strength, +23°C	7.5	kJ/m²	ISO 180/1A
Izod notched impact strength	4	kJ/m²	ISO 180/1A
Temperature	-20	°C	
Rockwell hardness	R 100		ISO 2039-2
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	57	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	114	°C	ISO 75-1/-2
Vicat softening temperature, A	148	°C	ISO 306
Vicat softening temperature, B	80	°C	ISO 306

TOTAL 10641

TotalEnergies

Other Properties	Value	Unit	Standard
Density	905	kg/m³	ISO 1183
Bulk density	525	kg/m³	