

**TECHNICAL DATA SHEET**

# TOTAL 7652

TotalEnergies

**Processing**

Injection molding

**Special Characteristics**

Anti-static

**Features**

Nucleated, Copolymer

**Applications**

Electrical and electrical, Toys

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	
Load	2.16	kg	

Mechanical Properties	Value	Unit	Standard
Tensile modulus	1450	MPa	ISO 527
Yield stress	26	MPa	ISO 527
Yield strain	10	%	ISO 527
Poisson's ratio	0.35		ISO 527
Flexural modulus, 23°C	1350	MPa	ISO 178
Charpy notched impact strength, +23°C	10	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	5.5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-20	°C	
Rockwell hardness	R 85		ISO 2039-2

Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	52	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, A	145	°C	ISO 306
Vicat softening temperature, B	75	°C	ISO 306

Other Properties	Value	Unit	Standard
Density	905	kg/m <sup>3</sup>	ISO 1183

# TOTAL 7652

TotalEnergies

Other Properties	Value	Unit	Standard
Bulk density	525	kg/m <sup>3</sup>	