



TER Plastics
POLYMER GROUP



Sarlink® 3139D - Shore 41 D

TPV

Teknor Apex Co.

Product Texts

Property	Value	Unit	Standard
Hardness Shore (5 sec delay, Extruded sample)	38D	-	ISO 868
Hardness Shore (5 sec delay, Injection molded sample)	41D	-	ISO 868
Tensile strength at break (Cross direction)	18.5	MPa	ISO 37
Modulus at 100% elongation (Cross direction)	8.9	MPa	ISO 37
Elongation at break (Cross direction)	700	%	ISO 37
Compression set (70h/125°C)	85	%	ISO 815
Hot air aging (168h/150°C, Cross Direction)			ISO 188
Change in hardness	1	points	
Retention tensile strength at break	93	%	
Retention modulus at 100% elongation	111	%	
Retention elongation at break	89	%	
Hot air aging (1000h/135°C, Cross Direction)			ISO 188
Change in hardness	0	points	
Retention tensile strength at break	95	%	
Retention modulus at 100% elongation	109	%	
Retention elongation at break	90	%	
Volume swell (70h/125°C in IRM 903 oil)	55	%	ISO 1817
Rheology (Apparent Shear Viscosity @ 206 1/s, 200°C)	310	Pa.s	ISO 11443 Capillary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at 100% elongation	13.3	MPa	ISO 527-1/-2
Strain at break TPE	>300	%	ISO 527-1/-2
Stress at break TPE	17.4	MPa	ISO 527-1/-2
Compression Set under constant strain, 23°C	53	%	ISO 815
Compression Set under constant strain, 70°C	67	%	ISO 815
Tear strength	101	kN/m	ISO 34-1

Other properties	Value	Unit	Test Standard
ISO Data			
Density	940	kg/m³	ISO 1183

Characteristics

Processing

Injection Molding, Other Extrusion, Blow Molding

Chemical Resistance

General Chemical Resistance