


**Sarlink® 3140 - Shore 46 A**

TPV

Teknor Apex Co.

**Product Texts**

Property	Value	Unit	Standard
Hardness Shore (5 sec delay, Extruded sample)	41A	-	ISO 868
Hardness Shore (5 sec delay, Injection molded sample)	46A	-	ISO 868
Tensile strength at break (Cross direction)	4.4	MPa	ISO 37
Modulus at 100% elongation (Cross direction)	1.2	MPa	ISO 37
Elongation at break (Cross direction)	600	%	ISO 37
Compression set (70h/125°C)	52	%	ISO 815
Hot air aging (168h/150°C, Cross Direction)			ISO 188
Change in hardness	1	points	
Retention tensile strength at break	111	%	
Retention modulus at 100% elongation	106	%	
Retention elongation at break	107	%	
Hot air aging (1000h/135°C, Cross Direction)			ISO 188
Change in hardness	-1	points	
Retention tensile strength at break	112	%	
Retention modulus at 100% elongation	105	%	
Retention elongation at break	112	%	
Volume swell (70h/125°C in IRM 903 oil)	135	%	ISO 1817
Rheology (Apparent Shear Viscosity @ 206 1/s, 200°C)	270	Pa.s	ISO 11443 Capillary

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at 100% elongation	2.5	MPa	ISO 527-1/-2
Strain at break TPE	210	%	ISO 527-1/-2
Stress at break TPE	2.5	MPa	ISO 527-1/-2
Compression Set under constant strain, 23°C	18	%	ISO 815
Compression Set under constant strain, 70°C	31	%	ISO 815
Tear strength	16	kN/m	ISO 34-1

Other properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Density	930	kg/m <sup>3</sup>	ISO 1183

**Characteristics**
**Processing**

Injection Molding, Other Extrusion, Blow Molding

**Chemical Resistance**

General Chemical Resistance