


**Sarlink® 6175N - Shore 76 A**

TPV

Teknor Apex Co.

**Product Texts**

Property	Value	Unit	Standard
Hardness Shore (5 sec delay, Extruded sample)	72A	-	ISO 868
Hardness Shore (5 sec delay, Injection molded sample)	76A	-	ISO 868
Tensile strength at break (Cross direction)	6.3	MPa	ISO 37
Modulus at 100% elongation (Cross direction)	3.2	MPa	ISO 37
Elongation at break (Cross direction)	641	%	ISO 37
Compression set (70h/125°C)	70	%	ISO 815
Rheology (Apparent Shear Viscosity @ 206 1/s, 200°C)	196	Pa.s	ISO 11443 Capillary

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at 100% elongation	4.3	MPa	ISO 527-1/-2
Strain at break TPE	>300	%	ISO 527-1/-2
Stress at break TPE	5.4	MPa	ISO 527-1/-2
Compression Set under constant strain, 23°C	33	%	ISO 815
Compression Set under constant strain, 70°C	48	%	ISO 815
Tear strength	33.2	kN/m	ISO 34-1

Other properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Density	926	kg/m <sup>3</sup>	ISO 1183

**Characteristics**
**Processing**

Injection Molding

**Features**

Low Fogging

**Delivery form**

Natural Color

**Chemical Resistance**

General Chemical Resistance

**Special Characteristics**

Heat stabilized or stable to heat

**Applications**

Automotive, Sports Equipment