

## TECHNICAL DATA SHEET

# Chemiton® GHB\_ \_ A75

Franplast

TPS

## Processing

Injection molding, Other extrusion

## Special Characteristics

U.V. stabilized or stable to weather

## Features

Copolymer

## Chemical Resistance

Ozone resistance

## Certifications

US Pharmacopeia class VI approved

## Applications

General purpose, Medical

| Mechanical Properties   | Value | Unit              | Standard   |
|-------------------------|-------|-------------------|------------|
| Tensile strength        | 11.6  | MPa               | ISO 527    |
| Strain at break TPE     | >300  | %                 | ISO 527    |
| Tear strength, parallel | 35.8  | kN/m              | ISO 34-1   |
| Shore A hardness, 15s   | 75    |                   | ISO 7619-1 |
| Other Properties        | Value | Unit              | Standard   |
| Density                 | 890   | kg/m <sup>3</sup> | ISO 1183   |