

TECHNICAL DATA SHEET

Chemiton® HMB_ _ A90

Franplast

TPS

Processing

Injection molding, Other extrusion

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat, Transparent

Features

Copolymer

Chemical Resistance

Ozone resistance, Radiation resistance

Certifications

US Pharmacopeia class VI approved

Applications

Automotive, Electrical and electronical, Medical

Mechanical Properties	Value	Unit	Standard
Tensile strength	18	MPa	ISO 527
Strain at break TPE	>300	%	ISO 527
Compression set at 23 °C, 24h	27	%	
Compression set at 70 °C, 24h	41	%	ISO 815
Tear strength, parallel	63	kN/m	ISO 34-1
Shore A hardness, 15s	90		ISO 7619-1
Other Properties	Value	Unit	Standard
Density	890	kg/m ³	ISO 1183