

TECHNICAL DATA SHEET

Vistamaxx™ 8880

ExxonMobil Chemical

TPO

Processing

Injection molding, Other extrusion

Pellets

Features

Good adhesion, Low odor

Delivery Form

Mechanical Properties	Value	Unit	Standard
Tensile strength at break	6.205	MPa	ExxonMobil Method
Elongation at break	1237	%	ExxonMobil Method
Modulus at 100% elongation	3.999	MPa	ExxonMobil Method
Thermal Properties	Value	Unit	Standard
Melting temperature	96.67	°C	ExxonMobil Method
Glass transition temperature	-21.67	°C	ExxonMobil Method
Other Properties	Value	Unit	Standard
Density	879	kg/m ³	ExxonMobil Method