

TECHNICAL DATA SHEET

Monprene® CP-17240

Teknor Apex Co.

TPE-X

Processing

Injection molding

Delivery Form

Pellets

Additives

Lubricants

Special Characteristics

U.V. stabilized or stable to weather, Opaque

Features

Good adhesion, Soft feel

Chemical Resistance

General chemical resistance

Applications

General purpose

Product Text

Product Information

Preliminary Data

The Monprene CP-17200 Filled, High Flow Series of thermoplastic elastomer compounds, with good UV resistance, available in NAT or colors, from 40 to 80 Shore A, are designed specifically for EU consumer product applications requiring a soft, rubber-like feel. Monprene CP-17240 is a low hardness, high density grade that is suitable for injection molding.

Adheres to PP

Property	Value	Unit	Standard
Apparent Viscosity (200 °C, 206 1/s)	109	Pas	ASTM D3835
Mechanical Properties		Value Unit	Standard
Modulus at 100% elongation		1 MPa	ASTM D 412
Modulus at 300% elongation		0.5 MPa	ASTM D 412
Shore A hardness		40	ASTM D 2240
Compression set, 22 hr @ 73 °F		20 %	ASTM D 395
Compression set, 22 hr @ 158 °F		38 %	ASTM D 395
Tensile strength at break		7.2 MPa	ASTM D 412
Elongation at break		900 %	ASTM D 412

Monprene® CP-17240

Teknor Apex Co.

Other Properties	Value	Unit	Standard
Density	1050	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Standard
Pre-drying - temperature	65	°C	
Pre-drying - time	2 - 4	h	
Melt temperature	180 - 230	°C	
Mold temperature	15 - 50	°C	
Zone 1	120 - 160	°C	
Zone 2	160 - 230	°C	
Zone 3	180 - 230	°C	
Nozzle temperature	180 - 230	°C	
Screw speed	50 - 100	rpm	
Back pressure	0.5 - 1.5	MPa	