

**TECHNICAL DATA SHEET**

# Monprene® RG-17260

Teknor Apex Co.

TPE-X

**Processing**

Injection molding

**Delivery Form**

Pellets

**Additives**

Lubricants

**Special Characteristics**

Opaque

**Features**

Good adhesion

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Packaging, Sports equipment

## Product Text

**Product Information**

Preliminary Data

The Monprene RG-17200 series is a group of high performance thermoplastic elastomers specifically designed for EU injection molded regulated applications including food contact, toys, and children's products. Monprene RG-17260 is a medium density, medium hardness grade that complies with various US FDA and European regulations and directives for food contact and toy safety and is suitable for injection molding.

Adheres to PP

Property	Value	Unit	Standard
Apparent Viscosity (200 °C, 206 1/s)	109	Pas	ASTM D3835
Mechanical Properties		Value Unit	Standard
Modulus at 100% elongation		2 MPa	ASTM D 412
Modulus at 300% elongation		0.7 MPa	ASTM D 412
Shore A hardness		60	ASTM D 2240
Tensile strength at break		8 MPa	ASTM D 412
Elongation at break		800 %	ASTM D 412
Compression set at 23 °C, 24h		26 %	
Compression set at 70 °C, 24h		47 %	ISO 815

# Monprene® RG-17260

Teknor Apex Co.

Other Properties	Value	Unit	Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183

  

Processing Recommendation Injection Molding	Value	Unit	Standard
Pre-drying - temperature	65	°C	
Pre-drying - time	2 - 4	h	
Melt temperature	180 - 230	°C	
Mold temperature	15 - 50	°C	
Zone 1	120 - 160	°C	
Zone 2	160 - 230	°C	
Zone 3	180 - 230	°C	
Nozzle temperature	180 - 230	°C	
Screw speed	50 - 100	rpm	
Back pressure	0.5 - 1.5	MPa	