

TECHNICAL DATA SHEET

# Arnitel® VT3104

Envalior  
TPC

**Processing**

Film extrusion, Profile extrusion, Sheet extrusion, Other extrusion

Pellets

**Certifications**

Food contact

**Delivery Form**

## Product Text

**Product Information**

Film Extrusion, Food Contact Quality

ISO 18064 TPC-ET


Processing/Physical Characteristics	Value	Unit	Standard
Melt volume-flow rate, MVR	13.5	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	
Load	2.16	kg	
Mechanical Properties	Value	Unit	Standard
Charpy notched impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eA
Stress at 10% elongation	4.4	MPa	ISO 527
Stress at 100% elongation	10.9	MPa	
Stress at break TPE	13.1	MPa	ISO 527
Tear strength, parallel	80	kN/m	ISO 34-1
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	212	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion, parallel	150	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	150	E-6/K	ISO 11359-1/-2
Electrical Properties	Value	Unit	Standard
Relative permittivity, 100Hz	4.7		IEC 62631-2-1

# Arnitel® VT3104

Envalior

Electrical Properties	Value	Unit	Standard
Relative permittivity, 1MHz	4.4		IEC 62631-2-1
Dissipation factor, 100Hz	310	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	810	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	20	kV/mm	IEC 60243-1
Comparative tracking index	600		IEC 60112
Other Properties	Value	Unit	Standard
Water absorption	7	%	Sim. to ISO 62
Humidity absorption	0.4	%	Sim. to ISO 62
Density	1160	kg/m <sup>3</sup>	ISO 1183

## Diagrams



## Processing Information

### Film extrusion

Recommendations For Extrusion Arnitel® VT Grades  
 Arnitel® Recommendations for Extrusion

### Other extrusion

Arnitel® Recommendations for Extrusion