

PBT/PET black with 30% glass fibre reinforcement and flame retardant V-0 quality.

TECHNICAL DATA SHEET

		STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm ³	1,67	
	Melt Flow Index	ISO 1133	gr/10 min.	-	
	Humidity Pelets	ISO 1110	%	0,2	
	Hardness	SHORE D	Points	80	
	Mold Shrinkage	-	%	-	

		STANDARD	UNIT	DRY	CONDITIONED
MECHANICAL	Tensile Strenth	ISO 527	N/mm ²	135	
	Elogantion at break	ISO 527	%	2	
	Tensile Modulus	ISO 527	N/mm ²	8500	
	Charpy Impact	23 °C ISO 179	Kj/m ²	42	
		-40 °C ISO 179	Kj/m ²	-	
	Charpy Impact	23 °C ISO 179	Kj/m ²	8	
-40 °C ISO 179		Kj/m ²	-		

		STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	10 ¹⁵	
	Dielectric strength	IEC 243	Kv/mm	31	
	Tracking index (C.T.I.)	IEC 112	Kv/mm	250	

		STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	221	
		(H.D.T.)	1,8 N ISO 75/A	°C	242
	VICAT Temperatura	ISO 306	°C	-	

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in - any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

V3.00/2021

	<i>STANDARD</i>	<i>UNIT</i>	<i>DRY</i>	<i>CONDITIONED</i>
OTHERS	UL - Flammability	UL-94	-	V-0
	Glow Wire	IEC 695	°C	960
	Fammability speed	FMV 302	mm/min.	<100
	Ashes	Triesa Test	%	~30
	Water absorption (24h)	ISO 62	%	~0,2
	Flame Retardant			YES

RECOMMENDED VALUES

PROCESSING	Drying Material	3h - 4h 110°C
	Mold. Temperature	90°C-110°C
	Processing Temperature	250°C-265°C
	Back Temperature	240°C-245°C
	Middle Temperature	250°C-255°C
	Nozzle Temperature	260°C-265°C
	Hold Pressure	60 - 90 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.