

EMERGE™ PC/ABS 7100 MED Advanced Resin

Overview

EMERGE™ PC/ABS 7100 MED Advanced Resin exhibits a balance of properties between impact strength, heat resistance and processability. It has excellent flow and is ideal for injection molding in thin-wall applications. This resin is available in natural and custom colors. EMERGE PC/ABS 7100 MED resin has been tested according to ISO 10993 (Biological Evaluation of Medical Devices) and is suitable for use in approved medical applications.

Main Characteristics:

- Tested under ISO 10993

Applications:

- Medical Applications

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.11 g/cm ³	1.11 g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238 ISO 1133
230°C/3.8 kg	4.5 g/10 min	4.5 g/10 min	
260°C/5.0 kg	25 g/10 min	25 g/10 min	
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	ASTM D955
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus ¹	321000 psi	2210 MPa	ASTM D638
Tensile Strength ² (Yield)	7300 psi	50.3 MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	4.0 %	4.0 %	
Break	50 %	50 %	
Flexural Modulus	339000 psi	2340 MPa	ASTM D790
Flexural Strength	11600 psi	80.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
-22°F (-30°C)	5.5 ft-lb/in	290 J/m	
73°F (23°C)	9.0 ft-lb/in	480 J/m	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-Scale)	112	112	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	241 °F	116 °C	
264 psi (1.8 MPa), Unannealed	203 °F	95.0 °C	
Vicat Softening Temperature	271 °F	133 °C	ASTM D1525 ³
CLTE - Flow (-40 to 104°F (-40 to 40°C))	4.2E-5 in/in/°F	7.6E-5 cm/cm/°C	ASTM D696
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating ⁴ (0.04 in (1.0 mm))	HB	HB	UL 94
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	176 to 194 °F	80 to 90 °C	
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr	
Processing (Melt) Temp	464 to 554 °F	240 to 290 °C	
Mold Temperature	122 to 194 °F	50 to 90 °C	