

PULSE™ 2000 EZ

PC/ABS Engineering Resin

Overview

Overview

PULSE™ 2000EZ is a high-heat PC/ABS resin delivering optimized performance for automotive interior component applications.

Benefits

- Easy flow, reduced scrap, and faster cycle times, while enabling thin wall part design for mass reduction.
- High-impact strength even at low temperature
- High Heat resistance for demanding automotive interior components
- Consistent natural white color produces high quality part appearance when used with color concentrates (self coloring) or Trinseo Color Masterbatch Technology
- Low odor & VOC to meet all global Automotive OEM specifications

Applications:

- Mid (floor)consoles
- Instrument Panel components
- Door panel trim
- Pillars
- Storage / load floors / glove box

Automotive Specifications

- 3M 11-0003-5762-1
- FORD WSS-M4D585-C1
- GM GMW15581P-ABS+PC-T6
- MERCEDES BENZ DBL 5404.29
- STELLANTIS MS-DB-195 CPN 2967
- STELLANTIS MS-DB-195 CPN 3401
- STELLANTIS MS-DB-195 CPN 4598
- TESLA TM-1003 10/20
- TOYOTA TSM 5526G-2
- VOLKSWAGEN TL 52231-A
- BMW GS 93016
- GM GMW15581P-ABS+PC-T3
- MERCEDES BENZ DBL 5404.28
- RNPO AS33
- STELLANTIS MS-DB-195 CPN 3159
- STELLANTIS MS-DB-195 CPN 3408
- STELLANTIS MS-DB-195 CPN 506
- TOYOTA TSM 5526G-1
- VOLKSWAGEN TL 52231
- VOLKSWAGEN TL 52231-B

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.13 g/cm ³	1.13 g/cm ³	ISO 1183
Apparent (Bulk) Density	0.66 g/cm ³	0.66 g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	18 g/10 min	18 g/10 min	ISO 1133
Spiral Flow ¹	18.5 in	47.0 cm	
Molding Shrinkage	4.0E-3 to 7.0E-3 in/in	0.40 to 0.70 %	ISO 294-4
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	348000 psi	2400 MPa	ISO 527-1/1
Tensile Stress (Yield)	7400 psi	51.0 MPa	ISO 527-2/50
Tensile Strain (Break)	120 %	120 %	ISO 527-2/50
Flexural Modulus ²	334000 psi	2300 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	12 ft·lb/in ²	25 kJ/m ²	
73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	223 °F	106 °C	ISO 75-2/A
Vicat Softening Temperature	262 °F	128 °C	ISO 306/B50
CLTE - Flow (-22 to 176°F (-30 to 80°C))	4.2E-5 in/in/°F	7.5E-5 cm/cm/°C	ISO 11359-2

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	491 to 554 °F	255 to 290 °C
Mold Temperature	140 to 176 °F	60 to 80 °C