

CALIBRE™ 200-6

Polycarbonate Resin

Overview

CALIBRE™ 200-6 polycarbonate resins are produced in compliance with the US Food and Drug Administration (FDA) and EU food contact regulations. They provide excellent impact resistance, heat distortion resistance and optical clarity as well as high melt strength for sheet extrusion applications. The CALIBRE 200-6 series products are available in 4 additive packages: CALIBRE 200: No mold release or UV Stabilizer. CALIBRE 201: Mold release. CALIBRE 202: UV stabilizer. CALIBRE 203: Mold release and UV stabilizer. . (Note that CALIBRE 202 and 203 grades are not available in Europe and do not comply with EU food contact regulations).

Govt. And Industry Standards:

- U.S. FDA 21 CFR 177.1580
- CSA
- Underwriters Laboratory (UL)
- EU food contact 2011/10/EC

Applications

- Small & large appliances
- Beverage containers/service ware
- Liquid containers
- Food processor housings
- Custom sheet
- Packaging applications

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.20 g/cm ³	1.20 g/cm ³	ASTM D792 ISO 1183/A
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238 ISO 1133
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	ASTM D955 ISO 294-4
Water Absorption			ASTM D570 ISO 62
24 hr, 73°F (23°C)	0.15 %	0.15 %	
Equilibrium, 73°F (23°C), 50% RH	0.32 %	0.32 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
-- ¹	350000 psi	2410 MPa	ASTM D638
--	334000 psi	2300 MPa	ISO 527-2/50
Tensile Strength			
Yield ¹	8700 psi	60.0 MPa	ASTM D638
Yield	8700 psi	60.0 MPa	ISO 527-2/50
Break ¹	10500 psi	72.4 MPa	ASTM D638
Break	10400 psi	72.0 MPa	ISO 527-2/50
Tensile Elongation			
Yield ¹	6.0 %	6.0 %	ASTM D638
Yield	6.0 %	6.0 %	ISO 527-2/50
Break ¹	150 %	150 %	ASTM D638
Break	150 %	150 %	ISO 527-2/50
Flexural Modulus			
-- ²	350000 psi	2410 MPa	ASTM D790
-- ³	348000 psi	2400 MPa	ISO 178

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Flexural Strength			
-- ₂	14000 psi	96.5 MPa	ASTM D790
-- ₃	14100 psi	97.0 MPa	ISO 178
Taber Abrasion Resistance	45 %	45 %	ASTM D1044
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			
73°F (23°C)	17 ft-lb/in	910 J/m	ASTM D256
73°F (23°C)	44 ft-lb/in ²	93 kJ/m ²	ISO 180/A
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D256 ISO 180
Instrumented Dart Impact ⁴			ASTM D3763
73°F (23°C), Total Energy	800 in-lb	90.4 J	
Tensile Impact Strength	280 ft-lb/in ²	588 kJ/m ²	ASTM D1822
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			ASTM D785
M-Scale	73	73	
R-Scale	118	118	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Annealed	293 °F	145 °C	ASTM D648
66 psi (0.45 MPa), Annealed	295 °F	146 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	265 °F	129 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	259 °F	126 °C	ISO 75-2/A
264 psi (1.8 MPa), Annealed	288 °F	142 °C	ASTM D648
264 psi (1.8 MPa), Annealed	289 °F	143 °C	ISO 75-2/A
Vicat Softening Temperature	304 °F	151 °C	ISO 306/B50 ASTM D1525 ⁵
Ball Indentation Temperature	257 °F	125 °C	IEC 60335-1
CLTE - Flow (-40 to 180°F (-40 to 82°C))	3.8E-5 in/in/°F	6.8E-5 cm/cm/°C	ASTM D696
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Volume Resistivity	2.0E+17 ohms-cm	2.0E+17 ohms-cm	ASTM D257
Dielectric Strength			
--	420 V/mil	17 kV/mm	ASTM D149
--	430 V/mil	17 kV/mm	IEC 60243-1
Dielectric Constant			ASTM D150
60 Hz	3.00	3.00	
1 MHz	3.00	3.00	
Dissipation Factor			ASTM D150
50 Hz	1.0E-3	1.0E-3	
1 MHz	2.0E-3	2.0E-3	
Comparative Tracking Index			IEC 60112
0.0787 in (2.00 mm), Solution A	250 V	250 V	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating ⁶			UL 94
0.06 in (1.6 mm)	HB	HB	
0.13 in (3.2 mm)	HB	HB	
Average Extent of Burning	1 in	3 cm	ASTM D635
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Refractive Index	1.586	1.586	ASTM D542 ISO 489
Transmittance	89.0 %	89.0 %	ASTM D1003
Haze	1.00 %	1.00 %	ASTM D1003