

CALIBRE™ IM 401-18

Polycarbonate Resin

Overview

CALIBRE™ IM 401-18 Impact Modified Polycarbonate resins is available in opaque formulations that offer benefits ranging from superior low temperature impact strength to easy processing with improved impact strength.

Main Characteristics:

- Impact modified
- Superior low temperature toughness

Applications:

- Automotive interiors
- Automotive exteriors
- Low temperature appliances

Automotive Specifications

- FORD WSB-M4D627-A
- GM GMP.PC.016
- STELLANTIS MS-DB-145 Type A CPN3102 Color: Black
- GM GMP.PC.004
- STELLANTIS MS-DB-145 CPN3101 Color: Gray
- STELLANTIS MS-DB-145 Type A CPN4483 Color: Natural

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.18 g/cm ³	1.18 g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	18 g/10 min	18 g/10 min	ASTM D1238 ISO 1133
Molding Shrinkage - Flow	6.0E-3 to 8.0E-3 in/in	0.60 to 0.80 %	ISO 294-4
Water Absorption			ISO 62
Saturation, 73°F (23°C)	0.32 %	0.32 %	
Equilibrium, 73°F (23°C), 50% RH	0.12 %	0.12 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			
Yield ¹	8400 psi	57.9 MPa	ASTM D638
Yield	8410 psi	58.0 MPa	ISO 527-2/50
Tensile Elongation			
Break ¹	110 %	110 %	ASTM D638
Break	110 %	110 %	ISO 527-2/50
Flexural Modulus			
--	331000 psi	2280 MPa	ASTM D790
... ²	329000 psi	2270 MPa	ISO 178
Flexural Strength			
--	13000 psi	89.6 MPa	ASTM D790
... ²	13100 psi	90.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	12 ft-lb/in	640 J/m	ASTM D256
Tensile Impact Strength	280 ft-lb/in ²	588 kJ/m ²	ASTM D1822

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed	250 °F	121 °C	
264 psi (1.8 MPa), Annealed	277 °F	136 °C	
Vicat Softening Temperature	295 °F	146 °C	ISO 306/B50 ASTM D1525 ³
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating ⁴			UL 94
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	248 °F	120 °C	
Drying Time	4.0 hr	4.0 hr	