

EMERGE™ PC 8310-10 Advanced Resin

Overview

EMERGE™ PC 8310-10 advanced resin is a transparent, ignition resistant PC resin, also available in opaque colors, that contains no chlorinated, brominated or phosphate flame retardant additives. The resin is designed to meet the German norm DIN VDE-0472/Part 815 on halogens. This resin combines good mechanical and high heat properties, maintains excellent processability and contains mold release agent. EMERGE™ PC 8310-10 advanced resin has a UL94 V-0 rating at 2.5 mm.

Applications:

- Electrical
- Information Technology Equipment
- Sockets, Plugs and Switches
- Lighting

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.20 g/cm ³	1.20 g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 g/10 min	10 g/10 min	ASTM D1238 ISO 1133
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	ASTM D955 ISO 294-4
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
-- ¹	334000 psi	2300 MPa	ASTM D638
--	348000 psi	2400 MPa	ISO 527-1/1
Tensile Strength			
Yield ²	8700 psi	60.0 MPa	ASTM D638
Yield	8700 psi	60.0 MPa	ISO 527-2/50
Break ²	9430 psi	65.0 MPa	ASTM D638
Break	8410 psi	58.0 MPa	ISO 527-2/50
Tensile Elongation			
Yield ²	6.0 %	6.0 %	ASTM D638
Yield	6.0 %	6.0 %	ISO 527-2/50
Break ²	120 %	120 %	ASTM D638
Flexural Modulus			
-- ³	348000 psi	2400 MPa	ASTM D790
-- ⁴	341000 psi	2350 MPa	ISO 178
Flexural Strength			
-- ³	13800 psi	95.0 MPa	ASTM D790
-- ⁴	13800 psi	95.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	17 ft-lb/in ²	35 kJ/m ²	ISO 179/1eA
Notched Izod Impact			
73°F (23°C)	13 ft-lb/in	700 J/m	ASTM D256
73°F (23°C)	33 ft-lb/in ²	70 kJ/m ²	ISO 180/1A

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Annealed	291 °F	144 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	259 °F	126 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	257 °F	125 °C	ISO 75-2/A
264 psi (1.8 MPa), Annealed	286 °F	141 °C	ISO 75-2/A
Vicat Softening Temperature			
--	306 °F	152 °C	ASTM D1525 ⁵
--	289 °F	143 °C	ISO 306/B50
Ball Indentation Temperature	> 257 °F	> 125 °C	IEC 60335-1
CLTE - Flow			
-40 to 176°F (-40 to 80°C)	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	ASTM D696
--	3.9E-5 in/in/°F	7.0E-5 cm/cm/°C	ISO 11359-2
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+15 ohms-cm	> 1.0E+15 ohms-cm	IEC 60093
Electric Strength	430 V/mil	17 kV/mm	IEC 60243-1
Dissipation Factor			IEC 60250
50 Hz	1.0E-3	1.0E-3	
1 MHz	2.0E-3	2.0E-3	
Arc Resistance	PLC 7	PLC 7	ASTM D495
Comparative Tracking Index			IEC 60112
0.0787 in (2.00 mm), Solution A	225 V	225 V	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating ⁶			UL 94
0.06 in (1.5 mm)	V-2	V-2	
0.10 in (2.5 mm)	V-0	V-0	
Glow Wire Flammability Index ⁶			IEC 60695-2-12
0.08 in (2.0 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature ⁶			IEC 60695-2-13
0.08 in (2.0 mm)	1470 °F	800 °C	
Oxygen Index ⁶	35 %	35 %	ISO 4589-2
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Light Transmittance	87.0 to 91.0 %	87.0 to 91.0 %	ASTM D1003
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	248 °F	120 °C	
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr	
Processing (Melt) Temp	518 to 572 °F	270 to 300 °C	
Mold Temperature	158 to 230 °F	70 to 110 °C	