

# STYRON™ 636 BT

## General Purpose Polystyrene Resin

### Overview

STYRON™ 636 BT is a general purpose polystyrene with a specific Blue Tone color designed for injection molded appliance applications. It is a high molecular weight material suitable for extrusion blending with high impact polystyrene. Its high strength makes it ideally suited for packaging applications and refrigerator accessories.

Applications:

- Injection molded appliance accessories and containers with a light blue tint
- Packaging foam extrusion
- Thermoformed containers blended with HIPS

Complies with:

- Europe REGULATION (EC)10/2011
- U.S. FDA 21 CFR 177.1640
- Consult the regulations for complete details.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm <sup>3</sup>	1.04 g/cm <sup>3</sup>	ISO 1183
Apparent (Bulk) Density	0.60 g/cm <sup>3</sup>	0.60 g/cm <sup>3</sup>	ISO 60
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.1 g/10 min	3.1 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	7980 psi	55.0 MPa	ISO 527-2/5
Tensile Strain (Break)	2.0 %	2.0 %	ISO 527-2/5
Flexural Modulus	479000 psi	3300 MPa	ISO 178
Flexural Stress	11600 psi	80.0 MPa	ISO 178
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness	21800 psi	150 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Annealed	194 °F	90.0 °C	ISO 75-2/A
Vicat Softening Temperature	206 °F	96.5 °C	ISO 306/A120
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating <sup>1</sup> (0.06 in (1.5 mm))	HB	HB	UL 94

### Additional Information

Mass balance versions (bio-based (BIO) or chemically recycled (CR)) of this product are chemically and physically indistinguishable to the standard fossil grade. This technical data sheet applies to all versions. Letters of sameness are available upon request.