

MAGNUM™ 3325 MT ABS Resin

Overview

Overview:

MAGNUM™ 3325MT is a medium heat ABS. Its inherent low gloss combined with a high flow makes it specifically suitable for unpainted interior automotive applications. It is globally available, locally produced in major car production regions.

Benefits:

- Lot to lot consistency allowing for optimal machine parameters settings from the start
- Self-coloring enabling improvement of costs by using less pigments and lowering your logistic costs
- Low VOC allowing a better interior air quality facing increasing regulatory and OEMs constraints.
- Heat stability during wide range of processing temperatures: enhanced part design freedom
- High scratch and mar resistance for an improved aesthetic durability of the parts
- Easier recyclability of unpainted part

Applications:

- Matt/unpainted interior automotive applications
- Mid-consoles
- Pillars
- Door Trims
- Glove boxes"

Automotive Specifications

- FORD ESB-M4D483-A2
- FORD WSS-M4D483-C1
- GM GMP.ABS.003
- JLR STJLR.51.353
- JLR STJLR.51.5262
- RNPO AS31
- STELLANTIS MS-DB-191 CPN 1734 Color: Color Match
- VOLKSWAGEN TL 527 Type A
- FORD WSK-M4D827-A
- FORD WSS-M4D827-C1
- GM GMW15572P-ABS-T2
- JLR STJLR.51.5229
- MERCEDES BENZ DBL 5404.80
- STELLANTIS MS-DB-191 CPN 1497 Color: Black
- TESLA TM-1002 10P
- VOLVO STD 1211,51

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.05 g/cm ³	1.05 g/cm ³	ISO 1183
Apparent (Bulk) Density	0.65 g/cm ³	0.65 g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR)			ISO 1133
220°C/10.0 kg	10 g/10 min	10 g/10 min	
230°C/3.8 kg	2.8 g/10 min	2.8 g/10 min	
Molding Shrinkage	4.0E-3 to 7.0E-3 in/in	0.40 to 0.70 %	ISO 294-4
VOC Content	35.0 µg/g	35.0 µg/g	VDA 277
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	268000 psi	1850 MPa	ISO 527-1/1
Tensile Stress (Yield)	5510 psi	38.0 MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	3.0 %	3.0 %	
Break	20 %	20 %	
Flexural Modulus ¹	268000 psi	1850 MPa	ISO 178
Flexural Stress ¹	8410 psi	58.0 MPa	ISO 178

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength 73°F (23°C), Injection Molded	7.6 ft·lb/in ²	16 kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength -22°F (-30°C)	4.8 ft·lb/in ²	10 kJ/m ²	ISO 180/1A
73°F (23°C)	8.1 ft·lb/in ²	17 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	174 °F	79.0 °C	ISO 75-2/A
Vicat Softening Temperature	210 °F	99.0 °C	ISO 306/B50

Additional Information

Mass balance versions (bio-based (BIO) or chemically recycled (CR)) of this product are chemically and physically indistinguishable to the standard fossil grade. This technical data sheet applies to all versions. Letters of sameness are available upon request.

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr