

TECHNICAL DATA SHEET

## TECHNYL B 218 BK 21N

TECHNYL B 218 BK 21N is an unreinforced copolyamide PA 66/6, heat stabilized, medium viscosity, for injection moulding . This grade offers an excellent combination between impact resistance, rigidity, thermal resistance and surface appearance.

### General

Polymer type	PA66/6 copolymer		
Certifications	RoHS EC 1907/2006 (REACH)	UL listed product	
Feature	heat-aging stabilized	good surface finish	
Applications	connectors		
Colors available	black		
Forms	pellets		
Processing technology	injection moulding		

### Product identification

ISO 1043 abbreviation	PA66/6
ISO 16396 designation	PA66/6,MH,S14-030

Condition	Standard	Unit	Value
-----------	----------	------	-------

### Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.14
Water absorption	24 hr, 23°C	ISO 62	%	1.6
Water absorption, saturation			%	3.6
Molding shrinkage, parallel		ISO 294-4, 2577	%	1.5
Molding shrinkage, normal		ISO 294-4, 2577	%	1.5

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3300 / 950
Stress at break		ISO 527-1/-2	MPa	75 / 30
Strain at break		ISO 527-1/-2	%	6 / 100
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	3100 / 900
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	120 / 35
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	4 / 15
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m <sup>2</sup>	4 / 15

\*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	242
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	180
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	55

	Condition	Standard	Unit	Value
<b>Burning behaviour</b>				
UL Yellow Card availability 1	<b><a href="#">Click here to have access to the UL Yellow Card availability 1 -&gt; QMFZ2.E44716</a></b>			
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

## Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E15
Dielectric strength	1 mm	IEC 60243-1	kV/mm	25.0

## Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	250 - 260 °C
Middle temperature	255 - 265 °C
Front temperature	265 - 275 °C
Recommended mould temperature	60 - 80 °C

## Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

## Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.